

E&C ADHESIVE 13111

■ Description

E&C ADHESIVE 13111 is a one-part, CFC-free, general purpose glue. It is a sprayable glue based on a synthetic rubber.



■ Application

E&C ADHESIVE 13111 has good adhesion to neoprene, natural and synthetic rubber, nylon, glass, ceramic, wood, PVC, insulation materials and most plastic materials. It can be used to attach foam absorbers to different substrates. It is the recommended adhesive to line ECCOSORB foam absorbers in anechoic chambers.

■ Physical properties

	E&C ADHESIVE 13111
Color	Brown
Solvent	Light inflammable (ethylacetate / acetone)
Density	0.8

E&C Anechoic Chambers NV
 Nijverheidsstraat 7A - B-2260 Westerlo
 Tel.: +32 14 59 58 00 - Fax: +32 14 59 58 01
 info@ecanechoicchambers.com
 www.ecanechoicchambers.com



E&C ADHESIVE 13111

■ Availability

E&C ADHESIVE 13111 is standard available in 1 liter and 5 liter containers.

■ Instructions for use

All surfaces to be bonded, except foam type absorbers and similar porous surfaces, should be cleaned of oil, grease and any foreign matter by means of a clean cloth dipped in an industrial cleaner degreaser solution.

Apply with good ventilation, avoid excessive breathing of vapours and wear individual adapted safety equipments.

- Shake well before opening and mix thoroughly before use.
- Best service temperature: 18 to 20°C.
- Sprayable glue. Both surfaces to be bonded, must be spray coated.
- Open time: 5 to 20 minutes according to applications. Apply sufficient pressure to ensure good contact to the mating surfaces.

Storage conditions:

Shelf life is 6 months when stored in closed, well sealed containers.

Conserve at a temperature of minimum 10°C in a dry place.

Transportation classification: UN1133, VP class II F1, GK 30GF1 - I+II.

Safety Considerations: It is recommended to consult the E&C ANECHOIC CHAMBERS product literature, including material safety data sheets, prior to use E&C ANECHOIC CHAMBERS products. These may be obtained from your local sales office.

WARRANTY: Values shown are based on testing of laboratory test specimens and represent data that falls within the normal range of properties of the material. These values are not intended for use in establishing maximum, minimum or ranges of values for specification purposes. Any determination of the suitability of the material or any use contemplated by the user and the manner of such use is the sole responsibility of the user who must assure that the material as subsequently processed meets the needs of this particular product or use.

We hope the information given here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale INCLUDING THOSE LIMITING WARRANTIES AND REMEDIES which apply to all goods supplied by us. We assume no responsibility for the use of these statements, recommendations or suggestions nor do we intend them as a recommendation for any use which would infringe any patent or copyright.

2010/04 - V01/1

E&C ANECHOIC CHAMBERS NV, Nijverheidsstraat 7A, B-2260 Westerlo, Belgium.

ECCOSORB is a registered trademark of EMERSON & CUMING Microwave Products NV.